





## R4K材料特性 · R4K Material Characteristics

特性 SYMBOL	测试条件 CONDITIONS		典型值 VALUE
初始磁导率 $\mu_i$ Initial permeability	10kHz, $B < 0.25\text{mT}$	25°C	$4300 \pm 25\%$
比损耗因子 $\tan \delta / \mu_i$ Relative loss factor	100kHz, $B < 0.25\text{mT}$	25°C	$< 10.0 \times 10^{-6}$
饱和磁通密度 $B_s$ ( mT ) Saturation flux density	50Hz, 1194A/m	25°C	450
剩磁 $B_r$ (mT) Residual flux density		25°C	140
矫顽力 $H_c$ (A/m) Coercive force		25°C	8
比温度系数 $\alpha \mu_r$ ( 1/°C ) Relative temperature coefficient		20°C ~ 60°C	$-0.5 \sim 2.0 \times 10^{-6}$
磁滞常数 $\eta_s$ ( /mT ) Hysteresis material constant	10kHz, 1.5~3mT	25°C	
居里温度 $T_c$ (°C) Curie temperature			$> 150$
电阻率 $\rho$ ( Ω · m) Resistivity			1.0
密度 $d$ ( g/cm³ ) Density			4.85



以上数据是根据标准样环  $\phi 25 \times \phi 15 \times 8$  获得的典型数据，有关产品的具体性能会在此基础上有所调整。  
The above typical data are calculated from the standard toroid core. Specific performance of the product will be adjusted on this basis.